

# Tjärfärg

This document applies to: Svarttjära, Svartbrun Tjära, Bruntjära, Gröntjära, Vittjära, Gultjära

## General

Auson Tjärfärg is based on pine tar. Our Pine Tar Products provide effective protection against water penetration and extend the lifespan of the wood. The strong tar scent fades after a few days and is barely noticeable after about a month.

Auson Pine Tar Products contain various resins and terpenes. Resins are the tree's natural defense against microorganisms and help to heal damage. Our pine tar is produced by heating resin-rich pine wood in a kiln. What makes our Pine Tar Products unique is their high tar content—read more in our brochure at [www.Tjarfarg.se](http://www.Tjarfarg.se).

## Areas of Use

Tjärfärg can be used on wood previously treated with distemper paint and iron vitriol, as well as on untreated or previously tar-treated wood such as wood paneling, wooden roofs, and other outdoor wooden structures.

## Application

Read the safety data sheet and the complete painting instructions at: [www.Tjarfarg.se](http://www.Tjarfarg.se)

## Packaging

0,1 liter can  
0,9 liter can  
2,7 liter can  
9 liter can

## Technical Data

Color:	(matte)
Density:	1,10 ± 0,03 kg/liter
Solids content (by weight):	82 % ± 3 %
Coverage:	5-8 m <sup>2</sup> /liter depending on the substrate
Drying time:	From a few days to several weeks depending on weather conditions, wood type, coating thickness, and how well the tar has penetrated the substrate
Thinner:	Gum turpentine or denatured alcohol (T-röd)
Cleaning:	Gum turpentine or denatured alcohol (T-röd)

For further information, see the safety data sheet or the instructions on the packaging.

Edition: 2026-04/27 / HA